

# SICOROL N

## COLOR DEEPENING, WATER-BASED IMPREGNATOR

### CHARACTERISTICS

SICOROL N is a color deepening, water-based impregnation product that displays no lasting gloss effect. It is delivered ready for use, creates a protective film and is very well-suited for lasting impregnation of concrete surfaces. The impregnated surface will repel dirt, oil, and water. SICOROL N is UV resistant, weather-proof and lessens the effects of scum on the concrete surface. SICOROL N increases resistance to the effects of freeze-thaw and de-icing salt. SICOROL N is able to penetrate deeply into the surface of concrete and has a good resistance against alkali reactions.

### AREAS OF APPLICATION

SICOROL N is specifically designed to protect paving, precast elements and cladding from liquid and oil-based contaminants. Both new and older, hardened concrete surfaces can be protected permanently. It is designed for use where an intensification of color is desired for the concrete surface without affectively sealing the surface. SICOROL N is particularly suitable for the treatment of absorbent concrete surfaces that have been previously finished by surface retarders, acid washing, sand blasting or hammering. It is not suitable for polished surfaces.

### GUIDANCE FOR APPLICATION

Before SICOROL N is applied, the surface to be treated must be thoroughly cleaned to remove contaminants, scum, algae and moss, as well as any traces of release agent from the formwork. This can be achieved by using our specially designed cleaner SICOROL ZE. The surface must be completely dry before SICOROL N is applied.

SICOROL N is best applied evenly and deeply to the surface using a roller. The application must be completed in one operation.

Further impregnation after the first coat is not possible because the fluid-repelling characteristics of the product will have taken affect.

Application is best carried out in dry weather with no wind. Air and surface temperatures should be between + 5°C and + 35°C. The surface to be treated should be protected from rain and strong sunlight during treatment and at least six hours after treatment. Conducting trials prior to final application is highly recommended.

### CONSUMPTION

Approx. **150 – 250 g/m<sup>2</sup>**

Exact consumption rate are dependent on the structure of the surface and absorbency of the concrete.

### TECHNICAL DATA

Form	liquid
Color	white
Density	approx. 1.01 g/cm <sup>3</sup>
Shelf life	1 year from date of manufacture
Storage	dry, protect from temperatures below 10°C and from direct sunlight
Container size	20 kg container 210 kg drum 1.000 kg container

### SAFETY

See European Union safety data sheet.

# FABRINO

Produktionsgesellschaft mbH & Co. KG | Augsburgener Straße 23 | D-87700 Memmingen  
TELEFON +49 (0)8331 92506-0 | TELEFAX -36 | info@fabrino.eu | www.fabrino.eu

02/15

Sämtliche Datenblätter beruhen auf als richtig und zuverlässig betrachteten Daten und Angaben und dienen dem Kunden zu Überprüfungs- und Nachweiszwecken, jedoch ohne Garantie unsererseits hinsichtlich erreichbarer Ergebnisse. Anforderungen die über den Rahmen des Datenblattes hinausgehen bedürfen zwingend der rechtsverbindlichen schriftlichen Bestätigung. Die Produktbeschreibung befreit den Anwender nicht von seiner Sorgfaltspflicht. Alle Rechte des Käufers richten sich nach unseren allgemeinen Geschäftsbedingungen.